

ALPHA ANALYTICS LIMITED

Results you can trust

 1/10A Hynds Road, Gate Pa Tauranga, BOP- 3112
 www.alphaanalytics.co.nz
 admin@alphaanalytics.co.nz
 Phone - 022 649 6707



ANALYTICAL REPORT

IDENTIFICATION OF ASBESTOS IN BULK SAMPLES

Client / Company name	AR PLUS	Sample address	5 Ron Miller Close
Client / Company address	32 Whiore Avenue, Tauriko, 3110		
Client contact	Jarrod McKeown	Lab reference code	B-05941
Sampler's name	Jarrod McKeown	Client reference code	5 Ron Miller Close
Sampler's contact number	+6427 475 5739	Date of sample reception	09-Jul-26
Email address	jarrod@arplus.nz	Date of Analysis	13-Jul-26
Date of sampling	09-Jul-26	Date of Reporting	13-Jul-26

RESULTS

Lab sample no.	Client sample no.	Sampling area details	Sample description	Sample quantity	Results
001	1	Decking	Cement	Acceptable	AMO, CHR
002	2	Textured Ceiling - Composite	Textured coating	Acceptable	CHR
003	3	House cladding	Cement	Acceptable	AMO, CHR
004	4	Decramastic roof	Bituminous product	Acceptable	CHR

Analytical Personnel: Meryn Tomson

Key Technical Personnel: Meryn Tomson

Notes

Method Summary: AS4964-2004 technique was used for identification of asbestos content in the submitted samples where the samples were first analysed using stereo microscopy and then by polarised light microscopy

Disclaimers:

- Alpha analytics is only involved in the analysis of submitted samples and is not involved in any sampling and do not provide guidance on sampling of asbestos containing materials to clients, and the results only apply to samples as received.
- The lab generated details includes the lab reference code, dates of sample reception, analysis, and reporting, lab sample number, names of analytical and key technical personnel, sample quantity, sample description and results only.
- Analytical test of swabs, tapes and wipe samples for asbestos content are outside the scope of the laboratory's accreditation.
- This certificate should only be interpreted and distributed in its complete form, and should not be duplicated or distributed partly.
- Samples and original COCs are stored only for 3 months. Electronic copies of results and worksheets are stored for 3 years

Fibre Legend:

CHR – Chrysotile (White asbestos)

ORG – Organic fibre

NAD – No asbestos detected

AMO – Amosite (Brown asbestos)

SMF – Synthetic mineral fibre

NFD – No fibre detected

CROC – Crocidolite (Blue asbestos)

UMF – Unknown mineral fibre