

ALPHA ANALYTICS LIMITED

Results you can trust

 1/10A Hynds Road, Gate Pa Tauranga, BOP- 3112
 www.alphaanalytics.co.nz
 admin@alphaanalytics.co.nz
 Phone - 022 649 6707



ANALYTICAL REPORT

IDENTIFICATION OF ASBESTOS IN BULK SAMPLES

Client / Company name	Zero Fibres Asbestos Consultants	Sample address	84 Harbour Road, Ohope
Client / Company address	30 Ohuirehe Rd, Whakatane		
Client contact	Joe Fenton	Lab reference code	B-04855
Sampler's name	Joe Fenton	Client reference code	84 Harbour Road, Ohope
Sampler's contact number	0212784703	Date of sample reception	17-Mar-26
Email address	joe@zerofibres.nz	Date of Analysis	18-Mar-26
Date of sampling	17-Mar-26	Date of Reporting	18-Mar-26

RESULTS

Lab sample no.	Client sample no.	Sampling area details	Sample description	Sample quantity	Results
001	1	Textured ceiling - Lounge	Textured Coating	Acceptable	NAD, ORG
002	2	Textured ceiling - Bedrooms x 2	Textured Coating	Acceptable	NAD, ORG
003	3	Textured ceiling - Hallway/Laundry	Textured Coating	Acceptable	NAD, ORG
004	4	Exterior cladding	Cement	Acceptable	NAD, ORG

Analytical Personnel: Meryn Tomson

Key Technical Personnel: Meryn Tomson

Notes

Method Summary: AS4964-2004 technique was used for identification of asbestos content in the submitted samples where the samples were first analysed using stereo microscopy and then by polarised light microscopy

Disclaimers:

1. Alpha analytics is only involved in the analysis of submitted samples and is not involved in any sampling and do not provide guidance on sampling of asbestos containing materials to clients, and the results only apply to samples as received.
2. The lab generated details includes the lab reference code, dates of sample reception, analysis, and reporting, lab sample number, names of analytical and key technical personnel, sample quantity, sample description and results only.
3. Analytical test of swabs, tapes and wipe samples for asbestos content are outside the scope of the laboratory's accreditation.
4. This certificate should only be interpreted and distributed in its complete form, and should not be duplicated or distributed partly.
5. Samples and original COCs are stored only for 3 months. Electronic copies of results and worksheets are stored for 3 years

Fibre Legend:

CHR – Chrysotile (White asbestos)	AMO – Amosite (Brown asbestos)	CROC – Crocidolite (Blue asbestos)
ORG – Organic fibre	SMF – Synthetic mineral fibre	UMF – Unknown mineral fibre
NAD – No asbestos detected	NFD – No fibre detected	